




Supi Saunasuoja (Sauna Finish)

Description	Water-borne tintable acrylate finish for interior surface treatment of humid rooms. Supi Sauna Finish seals surfaces against moisture and dirt. Contains anti-mould agent that protects the treated surface.
Product features	Suitable for use on wood, wood fibre board and concrete surfaces according to instructions for use.
Recommended uses	Especially suitable for walls and ceilings in steam, washing and dressing rooms. Not suitable for treatment of benches.



TECHNICAL DATA



Base paints	EP
Colour Range	Tikkurila interior wood stains and lacquers colour card.
Gloss grade	Semi-matt
Coverage	8-12 m ² /l.
Can sizes	0,9 l, 2,7 l, 9 l.
Thinner	Water
Application method	Brush or spray.
Curing	Dust dry after approx. 1/2 hour. The next coat can be applied after 2-3 hours. Ready for use in approx. two days.
Solids volume	Approx. 16 %.
Density	1.0 kg/l, ISO 2811.
Storage	Protect from frost.
Product code	868_6404

APPLICATION DETAILS

Application conditions	The surface to be painted must be dry, the temperature of the air at least +5°C, and the relative humidity of the air below 80 %.
Preparation	<p>New, clean wood surfaces:</p> <p>Remove all dirt and dust from surfaces. Moisten the surface lightly with a water spray, allow to dry and sand off any protruding wood fibres. Remove the sanding dust.</p>
Sauna protection	<p>Old and dirty or e.g. previously with Supi Sauna Finish treated surfaces:</p> <p>Wash with Supi Saunapesu Cleaning Agent according to instructions, rinse carefully and allow to dry. Sand if necessary and remove sanding dust.</p> <p>Stir SUPI Sauna Finish thoroughly before and occasionally during application.</p> <p>Apply one coat of tinted or untinted Supi Sauna Finish on the walls of steam room. Thin with water if necessary. You can also apply two coats of tinted Supi Sauna Finish thinned 50 % with water on the walls of steam room. This way the visible brush marks are minimized. Apply two coats of Supi Sauna Finish on the</p>



Supi Saunasuoja (Sauna Finish)

wood surfaces of washing and dressing rooms. Thin tinted Supi Sauna Finish 20 % with water for the first coat, thin clear product only if needed. Test the product on a piece of wood to ensure that the colour of the tinted product is correct. The colour appears lighter and more translucent than in the colour card, when the product is thinned. The final colour of the surface depends on timber species and the number of treatments. Treat small surfaces in one go to avoid overlapping; treat large panel surfaces a few boards at a time to get a uniform colour.

Surface treatment

Pre-heat the sauna before taking into use and ventilate it well.

Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu (Tool Cleaner) is recommended when cleaning hardened finish from the brush.

Maintenance instructions

At the earliest after 1 month from treatment.

EU VOC 2004/42/EC-limit value

Clean the surface with Supi Sauna Cleaning Agent (1-2 dl of cleaning agent into 5 litres of water).

(cat A/f) 130g/l(2010)

Supi Sauna Finish contains VOC max. 130 g/l.

HEALTH AND SAFETY LABELLING

according to Regulation (EC) No. 1272/2008

The product is not classified as dangerous. A Safety Data Sheet is available on request.

[Safety Data Sheet - SUPI SAUNASUOJA Sauna Finish](#)

ENVIRONMENTAL and WASTE DISPOSAL

Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations.

[Ympäristöseloste](#)

TRANSPORT

VAK/ADR: not classified

sre070612 / near141111 / lko141106 / tho031106 / 868 6404
